

What is claimed is:

1. An anti-static film for a display, comprising a hard coat layer provided on the surface of a transparent substrate directly or via another layer, wherein  
5 said hard coat layer contains at least resin, conductive material, and low refractive index material, surface electric resistance thereof is  $1.0 \times 10^{11} \Omega/\square$  or less, and the Y value thereof obtained by 5 degree specular reflectance is 4.0% or less.

10 2. An anti-static film for a display, in accordance with claim 1, wherein said low refractive index material has a particle size of 5 to 500 nm.

15 3. An anti-static film for a display, in accordance with claim 1, wherein said low refractive index material is contained at 15 to 200 weight parts to 100 weight parts of said conductive material.

4. An anti-static film for a display, in accordance with claim 1, wherein said low refractive index material is silica sol.

20 5. An anti-static film for a display, in accordance with claim 2, wherein said low refractive index material is silica sol.

6. An anti-static film for a display, in accordance with claim 3, wherein said low refractive index material is silica sol.

7. An anti-static film for a display, in accordance with claim 1, wherein said conductive material is metal oxide particles.

8. An anti-static film for a display, in accordance with claim 2, wherein  
5 said conductive material is metal oxide particles.

9. An anti-static film for a display, in accordance with claim 3, wherein said conductive material is metal oxide particles.

10. An anti-static film for a display, in accordance with claim 4, wherein said conductive material is metal oxide particles.

11. An anti-static film for a display, in accordance with claim 1, wherein an  
adhesion layer is further provided on a surface, in which said hard coat layer is  
not provided, of said transparent substrate, at least two layers of said layers are  
15 colored, and said colors are made to be achromatic by mixing.

12. An anti-static film for a display, in accordance with claim 2, wherein an  
adhesion layer is further provided on a surface, in which said hard coat layer is  
20 not provided, of said transparent substrate, at least two layers of said layers are  
colored, and said colors are made to be achromatic by mixing.

13. An anti-static film for a display, in accordance with claim 3, wherein an  
adhesion layer is further provided on a surface, in which said hard coat layer is

not provided, of said transparent substrate, at least two layers of said layers are colored, and said colors are made to be achromatic by mixing.

14. An anti-static film for a display, in accordance with claim 4, wherein an  
5 adhesion layer is further provided on a surface, in which said hard coat layer is not provided, of said transparent substrate, at least two layers of said layers are colored, and said colors are made to be achromatic by mixing.

15. An anti-static film for a display, in accordance with claim 7, wherein an  
10 adhesion layer is further provided on a surface, in which said hard coat layer is not provided, of said transparent substrate, at least two layers of said layers are colored, and said colors are made to be achromatic by mixing.